


OS-C12



Description

- Metal OD + reinforcement cap
- Non-spring-loaded sealing lip

Special features

- Non-spring-loaded lip design for secondary sealing jobs e.g., grease sealing
- Low friction
- Compact design
- Little installation space
- Firm and exact fit inside the housing
- Be careful when using the product in connection with light metal housings, housings with increased surface roughness and applications with overpressure: Apply sealing aid to the outside diameter if necessary. A version with outside diameter coated with bore sealant is available on request.

Applications e.g.:

- Secondary sealing jobs
- Mechanical and apparatus engineering
- Drive systems
- Electric motors

Materials

Standard material

Elastomer	NBR 70 black
Metal case	Carbon steel according to DIN EN 10139

Special materials

Elastomer	FKM
	Silicon
	ACM
	HNBR
	CR
	EPDM
Metal case	Stainless steel 1.4301

Application parameters

for the standard materials combination

Temperature	-40°C to +100°C
Pressure	depressurized
Shaft speed	max. 6 m/s , acc. to chart „Operating parameters for rotary shaft seals“
Media	Mineral oil based lubricants, synthetic lubricants

When synthetic lubricants are used for which there is no empirical experience, test the compatibility in the laboratory or - better even - in practical trials.
The operating temperature should not exceed 80°C.

Design information

Shaft

Tolerance	ISO h11
Hardness	min. 45 HRC
Roughness	$R_a = 0.2 - 0.8 \mu\text{m}$ $R_z = 1 - 5 \mu\text{m}$ $R_{\text{max}} \leq 6.3 \mu\text{m}$
Surface finish	free of orientation (lead free)

Housing bore

Tolerance	ISO H8
Roughness	$R_a = 0.8 - 3,2 \mu\text{m}$ $R_z = 6.3 - 16 \mu\text{m}$ $R_{\text{max}} \leq 16 \mu\text{m}$

Installation

Please read our installation instructions.